

PERM_S PermaStripe Smooth Data Sheet

Subject	Result	Test Method
Plastic composition	PVC	N/A
Plastic thickness	0.039in	N/A
Peel adhesion lbf/in	9.64	180° FINAT FTMI
Tensile strength, lbf/in	>45.7	Lloyd 112 lbf load cell
Adhesive thickness	0.008in	N/A
Total thickness	0.05in	N/A
Initial tack (in)	< 3	PSTC-6
180° Adhesion (lb/in)	>4.03	ASTM-D1000
Holding Power (hrs/kg/25.4mm ²)	>48	PSTC-7
Temperature range	-22°F to +158°F	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England.

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
PERM_NS (Black)	9004	Black 6 U	3.4	0.4
PERM_RS (Red)	3018	199 U	19.9	0.4
PERM_OS (Orange)	2008	021 U	36.2	0.6
PERM_YS (Yellow)	1018	108 U	64.6	2.9
PERM_VS (Green)	6018	Green U	30.1	1
PERM_BS (Blue)	5012	281 U	21	1.1
PERM_WS (White)	9003	7541 U	88.5	10.1
PERM_ZS (Black/ Yellow Hazard)	9004 / 1021	Black 6 U / 1235 U	3 / 61.8	0.5 / 0.5
PERM_AS (Red/ White Hazard)	3001 / 9003	485 U / 7541	1.1 / 77.4	1.1 / 1.2

All the above data is for reference only.

©Heskins LLC